

Item Description

Item ID

PRE-ELEC[®] PP 18220
PP18220

PP extrusion compound
Semiconductive
Surface quality

Typical end product
Cables

Applications
Conductor screen
Insulator screen

PRE-ELEC[®] PP 18220 is a semiconductive thermoplastic compound based on polypropylene for cable applications with good low temperature properties. The compound features premium surface quality and dispersion of carbon black. It is easy to extrude with high and consistent level of quality.

Special properties	Unit	Value	Method
Volume resistivity(*)	Ω.cm	25	PRE021

General properties	Unit	Value	Method
Density	g/cm ³	0,99	ISO 1183
Melt flow rate at 230°C 10,0 kg	g/10 min	3,2	ISO 1133
Vicat, Rate A	°C	97	ISO 306/A50
HDT, 0.45 MPa	°C	51	ISO 75/Bf
HDT, 1.80 MPa	°C	42	ISO 75/Af

Mechanical properties	Unit	Value	Method
Tensile strength(*)	MPa	35	ISO 527
Tensile strain at break(*)	%	400	ISO 527
Flexural modulus(*)	MPa	220	ISO 178
Tensile modulus	MPa	275	ISO 527
Impact strength, Charpy	kJ/m ²		ISO 179
Unnotched, +23°C		NB	
Notched, +23°C		NB	
Unnotched, -20°C		NB	
Notched, -20°C		84	
Hardness, Shore D(*)	-	51	ISO 868

MFR is measured from granulates. Tensile test speed: 25 mm/min, Sample test length 50mm
 Test specimen: injection moulded rod; ISO 527 TYPE 1A; Thickness: 10 mm, width: 4 mm
 (* extruded tape; ISO 527-2 Type 5A, thickness 400 - 800 µm)



Item Description
Item ID

PRE-ELEC[®] PP 18220
PP18220

Visit Premix Data Center for more detailed information of our products at
www.premixgroup.com/data-center/

Processing instructions

	Unit	Processing range
Extrusion		
Cylinder temperature profile	°C	170 - 210
Die temperature profile	°C	180 - 230
Tool/Roll temperature	°C	90 - 60

Notes

Drying of the product is recommended for 2-4 hours at 60-80°C prior to use.

These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] PP 18220 is a registered trademark of Premix.